1 - IDENTIFICATION OF THE MATERIAL AND SUPPLIER

Product Name	KLINGERSIL C-4430
Other Names	Compressed Non Asbestos Fibre Sheeting/Jointing/Gaskets
Recommended Use	High Temperature Gasket Material
Supplier	KLINGER Limited (ABN 95 008 679 838) 38 McDowell St Welshpool WA 6106 AUSTRALIA Tel +61 (0)8 9251 1600 or 1300 798 279 (0800 – 1700 Australian Western Standard Time – GMT +8 hrs) Fax +61 (0)8 9350 9286
Emergency Telephone Number	

2 - HAZARDS IDENTIFICATION

Not classified as hazardous according to the criteria of **Safe Work Australia** and **GHS** (Globally Harmonized System of Classification and Labelling of Chemicals).

Classification according to GHS:	Not Classified
GHS Label Elements:	Not Applicable for these products.
Other Hazard Information :	The product is considered harmless to health and the environment in the form supplied and if stored and handled in the correct manner – see Section 7. No hazards are known based on present information.

3 - COMPOSITION/INFORMATION ON INGREDIENTS

Ingredient	CAS	Proportion
Calcined Aluminia Silicate	92704-41-1	30 - 60%
Glass Fibre	65997-17-3	30 - 60%
Nitrile Butadiene Rubber	9003-18-3	10 - < 30%
Rock Wool Mineral Fibre	287922-11-6	10 - < 30%
Calcium Metasilicate (Wollastonite) 13983-17-0	10 - < 30%
Precipitated Silica	112926-00-8	< 10%
Aramid Fibre	26125-61-1	< 10%

4 - FIRST AID MEASURES

Inhalation	Dust arising from working the product should be treated as nuisance particulate material. Inhalation of dust may cause irritation to the mucous membranes and upper respiratory tract. Movement of exposed individual to fresh air is recommended.
Skin	May cause irritation to individuals with sensitive skin. Wash skin with soap and water. Launder heavily contaminated clothing before reuse. If prolonged irritation occurs, seek medical advice.
Eye	May cause mechanical irritation in contact with eyes. Remove small solid particles and rinse with water for a minimum of 15 minutes. In all cases of eye contamination it is a sensible precaution to seek medical advice.
Ingestion	Not hazardous. Not a likely source of exposure. If ingested, give plenty of fluid to assist passage through system. Seek medical attention if irritation occurs.

5 - FIRE FIGHTING MEASURES

Suitable Extinguishing Media	Water, carbon dioxide, powder extinguishers, foam extinguishers
Hazards from Combustion Products	In case of combustion, the same gases are produced as with burning rubber. The following may be produced in case of fire: Carbon monoxide; carbon dioxide; sulphur oxides; nitrous gases (NOx); irritating/caustic, combustible as well as poisonous carbonisation gases.
Precautions for Firefighters	
and Special Protective Equipment	Breathing apparatus and eye protection must be worn to protect from dust and fumes.

6 - ACCIDENTAL RELEASE MEASURES

Environmental: No known environmental hazards exist.

Methods and Materials for Containment and Cleanup	
	Approved vacuum cleaners with high efficiency filters (HEPA) conforming to AS3544 or equivalent must be used to clean areas. Spills which involve powder, dusts or granules may create a slip hazard and should be cleaned up immediately. Sweep up but avoid generating dusts.
Additional	In the case of improper use (see Section 8) fine dust may result. Adequate suction and filtering of the exhaust air should be ensured.

7 - HANDLING AND STORAGE

Handling No special precautions necessary when handling the material in its finished form However, whenever further processing of the product is undertaken, potential for the generation of dust exists. See Section 8.

StorageStore in a cool, dry, well ventilated area removed from foodstuffs.
Material is only flammable through the effects of intensive heat.
Excessive heat in the storage area may diminish the product's
performance in its intended application.

8 - EXPOSURE CONTROLS/PERSONAL PROTECTION

National Exposure Standards (Time-Weighted Averages)	Precipitated Silica: 10mg/m3 ES-TWA Nitrile Butadiene Rubber: 50ppm ES-TWA Aluminia Silicate: 10mg/m3 ES-TWA Glass Fibre: 0.5fibre/mL ES-TWA Rock Wool Mineral Fibre: 0.5fibre/mL ES-TWA Aramid Fibre: 0.5fibre/mL ES-TWA (Recommended - Note that Aramid fibre has no current assigned exposure standard, however as a general safety precaution the above guideline may be used.)
Biological Limit Value	No Biological Limit Value allocated.
Engineering Controls	Ensure adequate ventilation exists to maintain air concentrations below exposure standards. Do not inhale

dust. Use localised extraction or wet methods of work to control dust levels.

Personal Protective Equipment No special precautions necessary when handling the material in its finished form. However, whenever further processing of gaskets is undertaken, the potential for the release of particulates that may cause mechanical abrasion exists. In the case of particle generation exceeding the above-noted National Exposure Standards, recommended PPE are rubber/PVC gloves, coveralls, safety glasses and a P2 particulate (AS1716 or equivalent) respirator. When removing embrittled or spent material or when high levels or dust exist a full-face class H particulate cartridge respirator or full-face positive pressure demand airline respirator (AS1716 or equivalent) is recommended. Good hygiene practices must always be maintained.

9 - PHYSICAL AND CHEMICAL PROPERTIES

Appearance	Form: Colour:	Sheets or cut gaskets Green one side ,white other side
Odour	May smell sligh	ntly of rubber
рН	Not applicable	
Vapour Pressure	Not applicable	
Vapour Density	Not applicable	
Boiling Point/Range	Not applicable	
Freezing/Melting Point	Not applicable	
Flashpoint	Not-flammable	
Solubility (water)	Insoluble	
Specific Gravity/Density	1.75 g/cm3	
Additional	Elastomer carbo temperatures.	onisation and decomposition occurs at high

10 - STABILITY AND REACTIVITY

Chemical stabilityStable under intended operating conditions.Conditions to AvoidNot knownIncompatible MaterialsNot knownHazardous Decomposition
ProductsDecomposition of rubber at high temperatures.

11 - TOXICOLOGICAL INFORMATION

The material in its finished form presents no known health hazard. Synthetic mineral fibres (SMF) is a collective term used internationally to describe fibres such as fiberglass, rockwool and ceramic fibres. The release of SMF into the air is a health risk hence the adoption of an exposure standard of 0.5f/mL (TWA), for respirable fibres according to the National Commission – Worksafe Australia. For non-respirable SMF a secondary (complementary) exposure standard of 2mg/m3 is proposed by Worksafe Australia. This proposed secondary standard is established to minimise upper respiratory tract irritation from non-respirable fibres. It does not take precedence over the respirable fibre standard. Worksafe has determined not to classify SMF as a suspected carcinogen due to the lack of supporting evidence.

12 - ECOLOGICAL INFORMATION

Ecotoxicity	Not known. Insoluble in water, precipitates.
Persistence and Degradability	Not known. Not biologically degradable (self-classification).
Mobility	Not known

13 - DISPOSAL CONSIDERATIONS

Disposal Methods No special requirements exist. Dump on industrial depositories. Seal waste dust in heavy duty plastic bags (200 microns minimum). Do not dispose of in an incineration system under any circumstance. Local, state and federal statutory regulations must be observed.

Special Precautions Not applicable

14 - TRANSPORT INFORMATION

UN Number	None allocated
UN Proper Shipping Name	None allocated
Class and Subsidiary Risks	Not relevant
Packing Group	Not relevant
Special Precautions for User	Do not transport with Explosives, Oxidising agents, Organic peroxides and foodstuffs. In sheet and cut gasket form there is no risk associated with the product under normal transport conditions. Not defined as a Dangerous Good by the Australian Code for the Transport of Dangerous Goods by
	Road and Rail.

15 - REGULATORY INFORMATION

Regulations for dangerous materials not applicable.

16 - OTHER INFORMATION

Date of issue/revision: 04.02.21

All information and recommendations contained in this publication are based on the present level of knowledge and experience. Since the conditions of use are beyond our control, users must satisfy themselves that products are suitable for the intended processes and applications. No warranty is given or implied in respect of information and recommendations or that any use of the products will not infringe rights belonging to other parties. Our most current General Sales Conditions shall apply.

END OF MSDS